

1. Product Description

StenAst® 2EP-F is a two-component, solvent-free epoxy primer for all **Stenkim®** brand polymer-based surface coatings, topcoats and joint sealants. Its specially designed hardener gives it good adhesion. It protects the coated surface and prevents dusting.

2. Uses

StenAst® 2EP-F is a two-component, solvent-free, epoxy-based primer for materials and topcoats such as StenCoat®, StenSeal®, StenSport® and StenCare® that are applied to concrete, asphalt, steel, wood, epoxy and polyurethane surfaces. It is a water-impermeable primer for polyurethane surface coatings such as StenCoat® and StenSport® that are to be applied to outdoor asphalt and concrete floors. It ensures adhesion of polymer-modified cement-based materials applied to old concrete for repair or coating purposes. It is used to fill hairline cracks that form on the concrete surface and as a surface hardener and dust inhibitor for concrete pavements.

3. Application

3.1. Surface Preparation

Concrete Surfaces: The surface must be free from contaminants such as loose material, oil, grease and paint, and the concrete must be dry. This is especially important if a polyurethane material will be applied to the primed surface.

Relative humidity measured by hygrometer must be less than 75%; the absolute moisture content must be less than 3%. Surface moisture is not a problem where the product is used to ensure adhesion between old and new concrete. Contaminants adhering to the surface must be removed by sandblasting or grinding.

Contaminants that have penetrated into the concrete must be removed using cleaners capable of dissolving the contaminant, followed by cleaning with detergent and water. In areas where complete removal of contamination is uncertain, it is recommended to conduct an adhesion test before coating. **Steel Surfaces:**

Steel surfaces must be sandblasted and cleaned of all contamination, rust, and residues of previous coatings. The sandblasted surface must be primed without delay.

3.2. Application

It is recommended to condition the materials at 20-30 °C for one day before application. During application, surface and air temperature must be at least 10 °C and the temperature must not drop below 10 °C for 24 hours following the application. Component A of **StenAst® 2EP-F** is first mixed for 2-3 minutes on its own.

While mixing Component A in its container, pour Component B into the vortex and continue mixing at low speed for 2-3 minutes. A low speed drill is used for mixing. There must be no unmixed material left on the walls or at the bottom of the container. Then the mixture is transferred to a paint tray and applied continuously by working it into the floor with a brush or roller. If necessary, while the primer is still wet, dry aggregate of medium or coarse size can be sprinkled on it to create a non-slip, granular coating. It can be used to repair wide cracks in the application area by mixing the product with some quartz sand.

General Purpose Two-Component Filled Epoxy Primer

Highlights

- Provides good adhesion for further coating applications
- Fills microcracks in the concrete surface to form an impermeable layer
- Surface hardener that prevents dusting
- Can be applied with a brush and roller



Manual mixing of the components is insufficient. Insufficient mixing may cause the material to cure partially or not at all. Do not leave the mixed material in the mixing container. This significantly shortens the working time. Each coat is applied at a thickness of approximately 300-500 µm. Accordingly, the approximate consumption is 0.2-0.5 kg/m² per coat.

StenAst® 2EP-F is applied by brush or roller in one or two coats depending on the texture of the surface on which it is applied. The pot life of **StenAst® 2EP-F** and the required time before the next coat can be applied are as specified in the table. Here, the temperature of the surface on which the application is carried out is important.

It must be taken into account that the surface temperature may be higher than the ambient temperature in summer and lower in winter. During application, the surface temperature must be above 10 °C. If the primer application will be carried out as two coats, the second coat must be applied before the first coat is fully cured, while it is still tacky. If the second coat is applied too late, intercoat adhesion may be adversely affected.

3.3. Cleaning

Equipment used can be cleaned with **StenSolver EP** at the end of the job.

4. Safety

Applicators and supervisors must read the Safety Data Sheet (SDS) carefully and follow the instructions provided. Emptied packages must be disposed of in compliance with relevant regulations and laws. The application must be carried out by skilled workers under the supervision of experts and the applicators must use all personal protective equipment required for the worksite and the task such as goggles, mask and gloves.

5. Storage

Storage temperature must be between 5 and 30 °C. Packages must not be exposed to direct sunlight. Under these conditions, the material will retain its properties in unopened containers for 12 months from the production date.

Low temperatures may cause crystallization of the product; in this case, the product can be used after being warmed to +20 °C and homogenized. After prolonged storage, the product must be stirred thoroughly before use.

6. Disclaimer

This document is provided for general information and is based on **Stenkim®**'s laboratory data and field experience at the time of publication. **Stenkim®** reserves the right to revise this information without prior notice.

Stenkim® warrants that its products conform to the stated specifications on delivery. The buyer is responsible for determining the product's suitability for the intended purpose and for all conditions of transport, storage, application, and use. **Stenkim®** accepts no liability for results obtained under conditions outside its control. **Stenkim®**'s liability under this warranty is limited to replacement of non-conforming product and excludes any consequential or indirect damages.



7. Technical Data

Property	Method	Result
Base Polymer		Epoxy
Solids Content (by weight)	EN ISO 3251	100%
Color		Grey / Brown
Density	EN ISO 2811-2	1.46 ± 0.03 g/cm ³
Application Thickness (per coat)		300-500 µm
Pot Life @20 °C		70 ± 15 minutes
Tack-free Time @20 °C		3 hours
Ready for Light Foot Traffic @23 °C		24 hours
Minimum Overcoat Time @23 °C		2 hours
Maximum Overcoat Time @23 °C		24 hours
Full Cure Time		5-7 days
Shelf Life		1 year
Packaging		20 kg sets

Stenkim® reserves the right to make changes to the values in this table at any time. *CE: CE marked in accordance with EN 1504-2 (PR-C) (DoP STN-PRC-SA2EPF-0002).*

