

1. Product Description

StenCare® 3EP FN is a solvent-free, epoxy-based coating and repair material containing finely graded fillers, applied by pouring and designed for thin and shallow concrete repairs. It can be used as a two or three-component system. It has high adhesion and abrasion resistance, and is resistant to chemicals.

The polymeric mixture is compatible with thermal expansion of concrete made from Portland cement and adheres well to concrete. It is resistant to weak acids and alkalis, oils, fuels, antifreeze and many other chemicals.

2. Uses

StenCare® 3EP FN is used in repairing old concrete surfaces, broken slab and joint edges and similar locations. It is suitable for use on pedestrian walkways, industrial storage tank yard floors, airport pedestrian walkways, turning and deceleration zones in parking areas, and on concrete, mosaic, tile, wood, metal and asphalt surfaces in these spaces.

3. System Design

During system design, all aspects of the existing conditions and the application objective must be defined. **StenCare® 3EP FN** is suitable for thin and shallow repairs and for surface coatings; its fine filler content gives a smooth surface at low thicknesses. The maximum size of the aggregate to be used must not exceed half of the minimum application thickness.

4. Application

4.1. Surface Preparation

Proper surface preparation is of great importance. Oil, dirt, asphalt or old patch materials must not be left on the surface. Dust and loose materials must be removed. During application, the ambient and surface temperature must be between 15-30 °C, and the relative humidity of the surface must not exceed 75%.

4.2. Primer

The material itself can be used as a primer on clean concrete floors and in enclosed areas. In this case, 0.2-0.3 kg **StenCare® 3EP FN** is applied depending on the roughness of the surface. However, to increase adhesion strength substantially, it is recommended to first apply **StenAst® S**.

StenAst® S consumption is approximately 50 g/m². After application of **StenAst® S**, the floor becomes suitable for application of **StenCare® 3EP FN** within 30 minutes. Similarly, if another type of primer is required by surface characteristics, the application instructions of the primer must be followed.

4.3. Coating Application with Broadcast Aggregate

This method is used for the purpose of surface coating or thin surface repair. The mixture formed when Components A and B are mixed is self-leveling. It is of great importance that the surface to which this self-leveling material will be applied after mixing has been properly prepared.

**Two- or Three-Component,
Epoxy-Based, Finely Filled
Repair Mortar**

Highlights

- Withstands harsh conditions
- Non-slip
- 100% compatible with concrete
- Smooth, low-thickness repair with finely graded fillers
- Ideal for thin and shallow concrete repairs
- Resistant to chemicals
- Long-lasting and easy to apply



The components are mixed as follows. First, component A is mixed for 3-4 minutes. Then component B is added to the container holding component A, and the two components are mixed until homogeneous.

There must be no unmixed material left on the walls or at the bottom of the container. Mixing is carried out with a jiffy-type mixer and a powerful low-speed (300-500 rpm) machine. The mixing process must not be prolonged; it must be completed within 2-3 minutes, and the mixed material must not be left in the container. Otherwise, since the curing reaction is exothermic, the material in the container heats up and the curing rate increases. In this case, the mixed material in the container quickly solidifies and becomes unusable. However, since the material poured on the floor will be cooled by the floor, the reaction slows down, allowing the necessary time for application.

The mixture is poured onto the floor and applied with a steel or plastic notched trowel to a thickness of 2.0-2.5 mm. If desired, additional aggregate can be broadcast on the surface before the material sets. Aggregates must be selected among high hardness, abrasion-resistant materials. **StenSilica** #5-#10 (0.25-7 mm) is suitable for this purpose. Immediately afterwards, crushed aggregate sized from 1.5 to 4 mm is broadcast to create the desired surface texture. **StenSilica** #8-#9 is suitable for this purpose.

Loose aggregates on set material can be swept away. The aggregate size for the top layer is selected according to the desired surface roughness. After application of **StenCare® 3EP FN**, it is left to dry for 4 hours, and while this layer is still tacky, the actual coating is applied.

It is recommended to use **StenCoat® 2PUV 401**, 402 or 403 as the topcoat to increase the material's daylight resistance.

4.4. Repair Application with Aggregate Mixture

This method is primarily used to repair concrete pavements. For this purpose, heavy-duty Hilti-type or horizontal rotary mortar mixers must be used. Place Component A in the mixer, add Component B, and mix for 1-2 minutes until homogeneous. Component C is then added to this mixture and mixed for another 1-2 minutes, and immediately poured to the application site; first it is roughly spread and then leveled with a straightedge.

4.5. Cleaning

Equipment used can be cleaned at the end of the job with **StenSolver CL**.

5. Safety

Applicators and supervisors must read the Safety Data Sheet (SDS) carefully and follow the instructions provided. Emptied packages must be disposed of in compliance with relevant regulations and laws. The application must be carried out by skilled workers under the supervision of experts and the applicators must use all personal protective equipment required for the worksite and the task such as goggles, mask and gloves.

6. Storage

It must be stored away from open flames and ignition sources. Materials must be stored at 5-30 °C in a temperature-controlled environment, protected from daylight and moisture. Under these conditions, the material will retain its properties in unopened packages until the expiration date.

Low temperatures may cause crystallization of the product; in this case, the product can be used after being warmed to +20 °C and homogenized. After prolonged storage, the product must be stirred thoroughly before use.



7. Disclaimer

This document is provided for general information and is based on **Stenkim®**'s laboratory data and field experience at the time of publication. **Stenkim®** reserves the right to revise this information without prior notice.

Stenkim® warrants that its products conform to the stated specifications on delivery. The buyer is responsible for determining the product's suitability for the intended purpose and for all conditions of transport, storage, application, and use. **Stenkim®** accepts no liability for results obtained under conditions outside its control. **Stenkim®**'s liability under this warranty is limited to replacement of non-conforming product and excludes any consequential or indirect damages.

8. Technical Data

Property	Method	Result
Base Polymer		Epoxy
Solids Content (by weight)		100%
Color		Grey
Application Thickness		min. 2.5 mm
Hardness (Shore)	EN ISO 868	D80-85
Density (A+B+C)		2.2 ± 0.1 g/cm ³
Flame Resistance		Pass, does not ignite
Abrasion Resistance (A+B+C)	ASTM D 4060 CS10/1000 rev/1 kg	100 mg
Chemical Resistance; Jet Fuel, Motor Oil, Antifreeze, Salt @20 °C	ASTM D 1308	Pass
Pot Life @20 °C		60 ± 15 minutes
Tack-free Time @20 °C		3 hours
Ready for Light Foot Traffic @20 °C		12 hours
Time to Open to Heavy Traffic @20 °C		24 hours
Cure Time for Chemical Resistance @20 °C		5 days
Shelf Life		1 year
Packaging		24 kg sets

Stenkim® reserves the right to make changes to the values in this table at any time.

