

StenCoat® 2EPV 201 PLUS



1. Product Description

StenCoat® 2EPV 201 PLUS is an epoxy-based, two-component, transparent, decorative floor varnish. It has high abrasion and chemical resistance. It is resistant to outdoor conditions.

It is resistant to pool chemicals, weak acids and bases, detergents, disinfectants, hydraulic oils, many solvents and fuels. **StenCoat® 2EPV 201 PLUS** prevents dusting, abrasion, wetting and water permeation of the surface it protects, and increases its resistance to oxidation and soiling.

2. Uses

StenCoat® 2EPV 201 PLUS is a varnish used to improve chemical and abrasion resistance without changing the appearance of the floor. It also covers cracks and joints on concrete and metal floors, mortar type floor coatings, and coatings such as wood, tiles, granite, marble, natural stone and similar, increasing the durability and extending the life of the coating. Surfaces coated with **StenCoat® 2EPV 201 PLUS** are easy to clean, dry quickly, and do not generate dust.

The coating maintains its properties for a long time.

3. Surface Preparation

Application surfaces must be clean and dry. Surface temperature must not exceed 40 °C. **StenCoat® 2EPV 201 PLUS** can be used on glass, faience, ceramic, metal, brick and concrete surfaces without a primer.

For applications on polymeric surfaces, the surfaces should be primed with **StenAst® S**.

4. Application

It is recommended to condition the materials at 20-30 °C for one day before application. During application, surface and air temperature must be at least 10 °C and the temperature must not drop below 10 °C for 24 hours following the application. Application should not be carried out if there is a possibility of rain.

StenCoat® 2EPV 201 PLUS is prepared for the application by mixing two components. For easier application and a smoother surface, **StenSolver EP** can be added, not exceeding one part thinner to ten parts material. **StenSolver EP** must be added to component A at the beginning of the process, before component B is mixed in.

The components are packaged so that one container of each yields the correct mixing ratio. In cases where one complete package cannot be used, the package must be weighed and proportioned; the mix ratio stated on the package must be observed. Component B is added into the container of component A and they are mixed for 2-3 minutes at 300-500 rpm without letting air into the mixture.

Because the product is transparent, observe the mixing time closely to ensure the components are mixed homogeneously. Mixed material must be used within the pot life. Material that has begun to thicken must not be diluted for reuse.

Epoxy-Based Transparent Floor Varnish

Highlights

- Transparent
- Covers floor cracks and joints in wood, tile, granite, marble, natural stone and similar surfaces
- Unaffected by water and has excellent adhesion properties
- Highly resistant to abrasion and chemicals
- Easy to clean, dries quickly and does not cause dusting
- Forms a hygienic, clean and durable floor
- High chemical resistance and long service life



StenCoat® 2EPV 201 PLUS



StenCoat® 2EPV 201 PLUS is applied by spraying or by brush and roller. The desired surface texture depends on the method used and, if using a roller, the type of roller. When used as a standalone coating on concrete or similar surfaces, it is applied in one or two coats at 150-400 g/m² per coat.

5. Cleaning

Equipment used can be cleaned with **StenSolver EP** at the end of the job.

6. Safety

Applicators and supervisors must read the Material Safety Data Sheet (SDS) carefully and follow the instructions provided. Emptied packages must be handled in compliance with relevant regulations and laws. The application must be carried out by skilled workers under supervision of experts and the applicators must use all kinds of protective equipment required for the worksite and the task such as goggles, mask and gloves.

7. Storage

Storage temperature must be between 5 and 30 °C. Packages must not be exposed to direct sunlight. Under these conditions, the material will retain its properties in unopened containers for 12 months from the production date.

The product is flammable and combustible. Keep away from open flames and ignition sources. Low temperatures may cause crystallization of the product; in this case, the product can be used after heating and homogenizing at +20 °C.

The product must be stirred thoroughly before use after prolonged storage.

8. Disclaimer

This document is provided for general information and reflects **Stenkim®**'s laboratory data and field experience at the time of publication. **Stenkim®** reserves the right to revise this information at any time without notice.

Stenkim® warrants that its products conform to the stated specifications on delivery. The buyer is responsible for determining the product's suitability for the intended application and for all conditions of transport, storage, handling, and use. **Stenkim®** accepts no liability for results obtained under conditions outside its control. **Stenkim®**'s liability under this warranty is limited to replacement of non-conforming product and excludes any consequential or indirect damages.



StenCoat® 2EPV 201 PLUS



9 Technical Data

Property	Method	Result
Base Polymer		Epoxy
Solid Content		75
Color		Transparent
Density		0.99 ± 0.05 g/cm ³
Density (Dry Film)		1.04 ± 0.05 g/cm ³
Application Thickness (per coat)		100-300 µm
Abrasion Resistance	ASTM D 4060 CS17/1000 rev/1 kg	20 mg
Hardness	EN ISO 868	65-75 D
Adhesion Strength	ASTM D 4541 (on concrete)	> 430 psi (concrete fractures)
Adhesion Strength	ASTM D 4541 (on steel)	> 1500 psi
Pot Life @20 °C		75 minutes
Tack-free Time @20 °C		2 hours
Full Cure Time		3 days
Shelf Life		1 year
Packaging		15 kg sets

Stenkim® reserves the right to make changes to the values in this table at any time.



Stenkim Kimyasal Maddeler Sanayi ve Ticaret A.Ş.

Office: Portakal Cicegi Sok. Ansera Is Merkezi 17/126 Ayranci/ ANKARA Tel: +90 312 442 2630 Fax: +90 312 442 2615
www.stenkim.com.tr