

1. Product Description

StenCoat® 2PU TOP UV is a polyurethane-based, two-component, protective floor paint. **StenCoat® 2PU TOP UV** is resistant to abrasion, substrate movement and UV rays; it does not lose its flexibility and does not change color.

2. Uses

StenCoat® 2PU TOP UV is applied to polymeric floor coatings such as epoxy, polyurethane and polyurea to improve the resistance properties of the coating. Its flexibility, UV resistance, abrasion resistance, and slip resistance protect the coated surface.

3. Application

3.1. Surface Preparation

Application surfaces must be clean and dry. Application must not be carried out if the surface temperature is below 10 °C or above 40 °C. Epoxy and polyurethane substrates must be fully cured before the application.

3.2. Application

It is recommended to condition the materials at 20-30 °C for one day before application. During application, surface and air temperature must be at least 10 °C and the temperature must not drop below 10 °C for 24 hours following the application. Application must not be carried out if there is a possibility of rain.

StenCoat® 2PU TOP UV is ready for application when components A and B are mixed. The components are packaged so that one container of each yields the correct mixing ratio. In cases where a complete package will not be used, the package must be weighed and proportioned; the mix ratio stated on the package must be observed. Component B is added into the container of component A and they are mixed for 2-3 minutes at 300-500 rpm without entraining air in the mixture. Mixed material must be used within the pot life, and thickened material must not be thinned and reused.

StenCoat® 2PU TOP UV is applied by spraying or by brush and roller.

The application is carried out in one or two coats, with 200-400 g per m² per coat.

3.3. Cleaning

Equipment used can be cleaned at the end of the job with **StenSolver PU**.

4. Safety

Applicators and supervisors must read the Safety Data Sheet (SDS) carefully and follow the instructions provided. Emptied packages must be disposed of in compliance with relevant regulations and laws. The application must be carried out by skilled workers under the supervision of experts and the applicators must use all personal protective equipment required for the worksite and the task such as goggles, mask and gloves.

UV Resistant Elastic Polyurethane Paint

Highlights

- Can be used indoors and outdoors
- Not affected by UV rays emitted from sources such as the sun and halogen lamps
- Fully resistant to cleaning chemicals
- Flexible, adapts to substrate movement
- Can be used as a protective topcoat on all polymeric coatings such as polyurea, epoxy and polyurethane
- Can be used on all horizontal and vertical surfaces
- Easy to clean and dries quickly
- Easy to apply
- Long-lasting; does not crack, flake or peel
- Available in catalog colors



5. Storage

Storage temperature must be between 5 and 30 °C. Packages must not be exposed to direct sunlight. Under these conditions, the material will retain its properties in unopened containers for 12 months from the production date.

Low temperatures may cause crystallization of the product; in this case, the product can be used after being warmed to +20 °C and homogenized. After prolonged storage, the product must be stirred thoroughly before use.

6. Disclaimer

This document is provided for general information and is based on **Stenkim®**'s laboratory data and field experience at the time of publication. **Stenkim®** reserves the right to revise this information without prior notice.

Stenkim® warrants that its products conform to the stated specifications on delivery. The buyer is responsible for determining the product's suitability for the intended purpose and for all conditions of transport, storage, application, and use. **Stenkim®** accepts no liability for results obtained under conditions outside its control. **Stenkim®**'s liability under this warranty is limited to replacement of non-conforming product and excludes any consequential or indirect damages.

7. Technical Data

Property	Method	Result
Base Polymer		Two-Component Polyurethane
Solids Content (by weight)		65%
Color		Catalog
Density		1.3 ± 0.1 g/cm ³
Density (Dry Film)		1.6 ± 0.1 g/cm ³
Abrasion Resistance	EN ISO 5470-1	500 mg
Impact Resistance	EN ISO 6272-1	No Damage
Pot Life @20 °C		60 minutes
Tack-free Time @20 °C		2 hours
Full Cure Time		1 day
Consumption		200-400 g/m ²
Radiation Resistance	200 hours, Xenon Arc	No Damage
Shelf Life		1 year
Packaging		15 kg sets

Stenkim® reserves the right to make changes to the values in this table at any time.

