

1. Product Description

StenCoat® PUM 110 is a single-component, polyurethane-based, highly elastic, easy to apply, decorative waterproofing and protective coating. It is used for terrace, roof and wall waterproofing. It is applied as a liquid and forms an elastic, breathable, waterproof coating.

It is highly elastic and has crack-bridging ability. Therefore, it is resistant to cracks and movements that may occur on the substrate over time. Its mechanical properties do not change due to outdoor conditions. **StenCoat® PUM 110** complies with the ASTM C 836 waterproofing membrane standard.

2. Uses

StenCoat® PUM 110 is used in places such as terraces and under-roof areas, bathrooms and similar wet areas, industrial facilities and prefabricated structures. It can be applied vertically or horizontally on concrete, asphalt, steel or wooden surfaces.

3. Application

3.1. Surface Preparation

Application surfaces must be clean and dry. Loose materials must be removed and parts in disrepair must be repaired. Cracks must first be primed with **StenAst® S**.

Cracks wider than 1 mm must be filled with **StenSeal® PU 102** or **StenSeal® 2PU 210**. When applying over an existing waterproofing material, what that existing material is matters a great deal. For the right primer and application methods, contact **Stenkim®**.

3.2. Application

It is recommended to condition the materials at 20-30 °C for one day before application. During application, surface and air temperature must be at least 10 °C and the temperature must not drop below 10 °C for 24 hours following the application. **StenCoat® PUM 110** is ready for use and is applied without adding anything.

If thinning is necessary, only **StenSolver PU** can be used. Best results are achieved with two-coat application. In areas with severe conditions, an additional coat can be applied to increase total coating thickness. However, applications exceeding 2 mm in a single coat must not be performed. If the application environment is humid, the material must be applied in multiple thinner coats so that it is less affected by moisture.

StenCoat® PUM 110 can be reinforced with fiberglass mat or polyester felt. This type of application is particularly recommended on damaged surfaces, on substrates that have not yet settled, at wall-to-floor junctions, and at details such as pipe penetrations and drains. In such applications, complete saturation of the mat or felt with the material is very important. Reinforcement materials that are chemically incompatible or have water on their surface may damage the membranes.

Stenkim® offers free consultancy and analysis services for selection of the correct reinforcement materials and approval of the material to be used. **StenCoat® PUM 110** is applied at 0.7-2.9 kg/m² per coat depending on the

Polyurethane-Based Elastomeric Liquid Waterproofing Membrane

Highlights

- Elastomeric
- Single-component and ready-to-use
- Seamless; provides long-lasting waterproofing
- Bridges cracks thanks to its high elasticity
- Has high chemical resistance; does not undergo hydrolysis and does not separate from the surface
- Easy to apply, seamless, and does not require a torch
- Saves application labor and offers an economic advantage through long service life
- Available in catalog colors



desired coating thickness; however, for the same film thickness, the required amount may increase on rough surfaces. In applications with a mat, consumption per square meter increases in proportion to the absorbency of the mat.

3.3. Cleaning

Equipment used can be cleaned at the end of the job with **StenSolver PU**.

4. Safety

Applicators and supervisors must read the Safety Data Sheet (SDS) carefully and follow the instructions provided. Emptied packages must be disposed of in compliance with relevant regulations and laws. The application must be carried out by skilled workers under the supervision of experts and the applicators must use all personal protective equipment required for the worksite and the task such as goggles, mask and gloves.

5. Storage

Packages must not be exposed to direct sunlight. It must be stored away from open flames and ignition sources. Storage temperature must be between 5 and 30 °C. Under these conditions, the material will retain its properties in unopened containers for 6 months from the production date. The material is flammable. Low temperatures may cause crystallization of the product; in this case, the product can be used after being warmed to +20 °C and homogenized. After prolonged storage, the product must be stirred thoroughly before use.

6. Disclaimer

This document is provided for general information and is based on **Stenkim®**'s laboratory data and field experience at the time of publication. **Stenkim®** reserves the right to revise this information without prior notice.

Stenkim® warrants that its products conform to the stated specifications on delivery. The buyer is responsible for determining the product's suitability for the intended purpose and for all conditions of transport, storage, application, and use. **Stenkim®** accepts no liability for results obtained under conditions outside its control. **Stenkim®**'s liability under this warranty is limited to replacement of non-conforming product and excludes any consequential or indirect damages.



7. Technical Data

Property	Method	Result
Base Polymer		Single-Component Polyurethane
Solids Content (by weight)		100%
Application Thickness (per coat)		500-2000 µm
Color		Catalog
Density		1.44 ± 0.05 g/cm ³
Hardness	EN ISO 868	A20-25
Elongation at Break	ASTM D 412 Die B	600%
Impact Resistance	EN ISO 6272-1	≥ 20 Nm (No Damage)
Peel Strength	ASTM C 794, 7 days in water	200 N/m
Low Temperature Crack Bridging	ASTM C 1305	Pass
Flexibility After Thermal Aging	ASTM C 1522	Pass
Tensile Modulus (100% Elongation)	ASTM D 412	0.46 MPa
Cure Rate @20 °C, 50% RH		2 mm/24 hours
Tack-free Time @20 °C		4 hours
Minimum Overcoat Time @20 °C		2 hours
Maximum Overcoat Time @20 °C		24 hours
Full Cure Time (2 mm Coating)		2 days
Shelf Life		6 months
Packaging		23 kg packages

Stenkim® reserves the right to make changes to the values in this table at any time.

