

1. Product Description

StenMix® AER is an air-entraining admixture that distributes the air in the concrete as controlled micro pores and increases the concrete's resistance to freeze/thaw cycles. **StenMix® AER** conforms to the requirements of EN 934-2 Table 5 (Air-Entraining Admixture for Concrete) and ASTM C 260 (Standard Specification for Air-Entraining Admixtures for Concrete).

2. Uses

StenMix® AER is used in concrete roads, airports, runways and aprons, dams and water reservoirs, and watertight mass concrete. It can also be used in the production of all types of reinforced/unreinforced, lightweight/normal-weight concrete and in mass concrete production. **StenMix® AER** can be used for producing concrete with high workability and high durability, in concrete masses exposed to winter conditions and deicing salts, in places where freeze/thaw cycles are frequent, and in places where air-entrained concrete is required.

3. Application

StenMix® AER is a ready-to-use liquid. It can be mixed with concrete directly. Depending on the desired amount of entrained air, it must be used at 0.03% to 0.15% based on the weight of cement.

The dosage must be determined by air meter tests in trial mixes, considering aggregate size distribution, water/cement ratio, type, fineness and dosage of cement and ambient temperature. Increased entrained air content may have an adverse effect on concrete strength. (A 5% loss in final strength must be anticipated for each additional 1% of air.) This adverse effect on concrete strength can be compensated by using StenMix® series water-reducing and strength-enhancing admixtures together with air-entraining agents.

4. Safety

Applicators and supervisors must read the Safety Data Sheet (SDS) carefully and follow the instructions provided. Emptied packages must be disposed of in compliance with relevant regulations and laws. The application must be carried out by skilled workers under the supervision of experts and the applicators must use all personal protective equipment required for the worksite and the task such as goggles, mask and gloves.

5. Storage

The material must be kept in dry indoor storage. Protect the product from freezing. Shelf life is 1 year in unopened packaging.

Products must be stored at +5 °C to +35 °C in enclosed storage protected from direct sunlight. Low temperatures may cause crystallization of the product; in this case, the product can be used after being warmed to +20 °C and homogenized. After prolonged storage, the product must be stirred thoroughly before use.

Air Entraining Concrete Admixture

Highlights

- Ensures controlled distribution of air in concrete in the form of micropores
- Increases concrete's resistance to freeze-thaw cycles
- Reduces the risk of segregation in concrete
- Allows production of concrete with high workability and high durability
- Used in locations exposed to winter conditions and in watertight mass concrete
- Used where air-entrained concrete is required
- Can be used in production of all types of reinforced/unreinforced, lightweight/normal weight concrete and concrete blocks
- Ideal for locations such as concrete roads, airports, runways, aprons, dams and water reservoirs



6. Disclaimer

This document is provided for general information and is based on **Stenkim®**'s laboratory data and field experience at the time of publication. **Stenkim®** reserves the right to revise this information without prior notice.

Stenkim® warrants that its products conform to the stated specifications on delivery. The buyer is responsible for determining the product's suitability for the intended purpose and for all conditions of transport, storage, application, and use. **Stenkim®** accepts no liability for results obtained under conditions outside its control. **Stenkim®**'s liability under this warranty is limited to replacement of non-conforming product and excludes any consequential or indirect damages.

7. Technical Data

Property	Method	Result
Appearance - Color		Light-colored liquid
Chemical Composition		Synthetic Surface-Active Agent
Density @20 °C	EN ISO 2811-2	1.01 ± 0.01 g/cm ³
pH	ISO 4316	7 ± 1
Chloride Content	EN 480-10	None
Freezing Point	ISO 3016	0 °C
Shelf Life		1 year
Packaging		200 kg drums or 1,000 kg IBCs

Stenkim® reserves the right to make changes to the values in this table at any time. *CE: CE marked in accordance with EN 934-2:2009+A1:2012 (DoP STN-AER-0002).*

