

1. Product Description

StenSeal® SI 110 is a single-component, cold-applied, self-leveling, low modulus silicone joint sealant. It is specially formulated for outdoor concrete pavements and provides excellent resistance to all weather conditions, heavy traffic, jet blast, and intermittent chemical contact. **StenSeal® SI 110** is highly durable and remains resistant to fuels, hydraulic fluids, and oils, as well as dynamic movement. It is also highly resistant to UV radiation and extreme temperatures. **StenSeal® SI 110** is fully compliant with ASTM D 5893, Type SL, ASTM C 920, Type S, Grade P, Movement Class 100 and EN 14188-2, System S, Class A, Type SL. Compliance with ASTM D 5893 has been certified by PRI.

2. Uses

StenSeal® SI 110 is ideal for use in horizontal joints and cracks with a constant width. It is particularly well-suited for use in the joints of airports, roads, bridges, refineries, and chemical facilities, as well as for expansion and contraction joints in asphalt or cement concrete pavements. **StenSeal® SI 110** adheres to properly prepared joints without a primer.

Its self-leveling property provides better adhesion and a smoother surface profile compared to non-sagging types. **StenSeal® SI 110** is preferred for use in freshly cut concrete joints with a constant width and straight edges. For cracks and joints with irregular cross-sections or variable widths, and for sloped or vertical joints, the non-sagging type **StenSeal® SI 111** may be more suitable.

3. Joint Design

The pavement should be designed and joints sized so that the maximum extension and compression do not exceed +100% and -50%, respectively. Joint spacing, the coefficient of thermal expansion of the pavement, expected temperature range, and the anticipated temperature at the time of sealing must all be considered. For controlling shrinkage cracks that will form in new concrete pavements, distance, width, depth, and sealing time of the contraction joints are all crucial.

Refer to our technical document for further information on joint design and crack control. The minimum width of a joint must be at least twice the expected movement of the pavement. The width of the joints must be between 6.35 mm and 38.1 mm. For joint widths outside of these bounds, contact **Stenkim®**. The sealant depth must be half of the width and between 6.35 mm and 12.7 mm. If the calculated depth is outside of these bounds, it must be adjusted to the nearest limit.

Single-Component, Self-Leveling Silicone Joint Sealant

Highlights

- Low hardness and high elongation
- Movement Class 100/50
- Suitable for horizontal joints
- Self-levels to provide better adhesion and surface profile
- Primer-free application
- Adheres to asphalt and concrete surfaces
- Long-lasting
- Resistant to jet fuels, oils, diluted acids and bases, and various chemicals
- Resistant to UV radiation and does not discolor
- Resistant to jet blast and high temperature
- Ready to use and easy to apply
- Ideal for airports, highways, and large outdoor surfaces



Joint Width (mm)	8	10	12	14	16	18	20	24	28	32	36
Sealant Thickness - mm	7	7	7	7	8	9	10	12	13	13	13
Sealant Recess - mm	7	7	7	8	9	10	11	13	13	13	13
Backer Rod Diameter - mm	10	13	15	18	20	23	25	30	35	40	45
Minimum Backer Rod Depth - mm	14	14	14	15	17	19	21	25	26	26	26
Consumption - meters / tube	10.5	8.4	7	5.6	4.2	3.5	2.8	1.4	1.4	1.4	0.7
Consumption - meters / bucket	307	246	205	175	134	106	86	60	47	41	37

4. Application

4.1. Surface Preparation

The joint surfaces must be clean and dry, and any oil, grease, bitumen, or old sealant residues must be completely removed. Loose material on the joint edges must be removed; broken joint edges must be repaired. The surfaces can be sandblasted for better adhesion. **StenSeal® SI 110** does not adhere to wet surfaces as well as dry surfaces, so the joints must be dry and the sealant must not contact water until the end of the skin-over time.

4.2. Primer

StenSeal® SI 110 must be applied to cement concrete and asphalt concrete joints without a primer. For other types of surfaces, a primer may be necessary. Contact **Stenkim®** for guidance.

4.3. Backer Material

To attain the sealant depth and recess, a backer rod that preferably does not adhere to the sealant must be placed in the joint. Since the joint will not be filled to the top edge, the backer rod must be positioned at a depth equal to the calculated sealant depth plus the recess depth. For self-leveling sealants, it is important that the backer rod fits tightly along the joint length.

Closed-cell polyethylene foam rods are suitable for this purpose. The diameter of the backer rod must be 10-25% larger than the joint width, and the rod must be placed tightly in the joint. In wide joints, semi-rigid materials, such as polystyrene foam, can be used instead of a backer rod. In such cases, it is helpful to place a polyethylene tape over the backing material to prevent adhesion to the sealant.

4.4. Application

The sealant can be installed from 4 °C to 41 °C, but the temperature must be above the dew point. The sealant must be protected from rain, liquids and dust until the skin-over time has elapsed. The skin formation time for **StenSeal® SI 110** is at most 120 minutes, and the time to reach ultimate properties is 2 weeks.

Higher temperature and humidity accelerate skin formation and full cure. The sealant can be applied directly from 18.1 l cans or 189 l or 199.5 l drums using a pump, or it can be transferred to a hand pump. 600 ml tubes must be cut on one end and placed in a caulking gun.

While the sealant is being applied, the tip of the gun must be moved forward by sliding over the backer rod in the joint. The application pump or the caulking gun must have a nozzle appropriate to the joint width. There must be no air gaps under the sealant or between joint surfaces and the sealant.



Once a sufficient amount of sealant has been applied, it will self-level and no tooling is required. The sealant surface must remain approximately 6.35 mm to 12.7 mm below the top edge. Consumption of the sealant must be monitored to ensure correct sealant depth and recess.

Adequate ventilation is required for indoor applications. **StenSeal® SI 110** must not be used in unventilated spaces.

4.5. Application Tools

Drum pumps, application guns or tube guns, and spatulas are necessary for proper application. Professional quality tools must be used.

4.6. Cleaning

Application equipment and any other equipment contaminated with sealant must be cleaned before the sealant cures. For that purpose, tools must first be wiped with a cloth or rag and then cleaned with **StenSolver CL** or aromatic solvents such as toluene and xylene. Proper protective equipment and ventilation must be used when handling these solvents.

Cured **StenSeal® SI 110** can only be removed by mechanical means.

5. Safety

Applicators and supervisors must read the Safety Data Sheet (SDS) carefully and follow the instructions provided. Emptied packages must be disposed of in compliance with relevant regulations and laws. The application must be carried out by skilled workers under the supervision of experts and the applicators must use all personal protective equipment required for the worksite and the task such as goggles, mask and gloves.

6. Storage

StenSeal® SI 110 must be kept in dry indoor storage with a recommended temperature range of 10 °C to 32 °C. If stored unopened in these conditions, the shelf life is at least 12 months. Avoid storing the sealant in high humidity conditions or at temperatures above 38 °C for prolonged periods of time.

If the sealant has been stored inappropriately, or the storage period has been exceeded, the product must be checked before use.

7. Disclaimer

This document is provided for general information and is based on **Stenkim®**'s laboratory data and field experience at the time of publication. **Stenkim®** reserves the right to revise this information without prior notice.

Stenkim® warrants that its products conform to the stated specifications on delivery. The buyer is responsible for determining the product's suitability for the intended purpose and for all conditions of transport, storage, application, and use. **Stenkim®** accepts no liability for results obtained under conditions outside its control. **Stenkim®**'s liability under this warranty is limited to replacement of non-conforming product and excludes any consequential or indirect damages.



8. Technical Data

Property	Method	Result
Base Polymer		Single-Component Silicone
Solids Content (by weight)		98%
Color		White / Grey / Black / Red / Blue
Density	ASTM D 1475	1.20 ± 0.05 g/cm ³
Rheological Property (flow)	ASTM C 639	Smooth, level surface
Extrusion Rate	ASTM C 1183	> 200 ml/min
Tack-free Time @20 °C	ASTM C 679 / EN 14187-1	< 120 minutes
Cure Rate @20 °C		3.2 mm/day (1/8 inch/day)
Weight Loss on Heat Aging	ASTM C 792	< 3%
Hardness	ASTM D 2240	> 70 Shore OO (@23 °C) / < 20 Shore A (@-29 °C)
Flow at High Temperature (93 °C)	ASTM D 5329	No flow
Elongation at Break	ASTM D 412 / EN ISO 8339	> 700%
Tensile Stress at 150% Elongation	ASTM D 412 / EN ISO 8339	< 25 psi (< 0.17 MPa)
Elastic Recovery	ASTM D 5893	> 90%
Accelerated Weathering (5000 hours)	ASTM C 793	Pass
Bond Strength (conditioned at -29 °C, 5 cycles at 100% extension)	ASTM D 5893	Pass
Bond Strength (water-immersed, 5 cycles)	ASTM D 5893	Pass
Bond Strength (heat-aged, 5 cycles)	ASTM D 5893	Pass
Flame Resistance (260 °C, 120 s)	SS-S-200E (3.4.8)	Pass
Movement Capability (extension/compression)	ASTM C 920 / EN ISO 11600	+100% / -50% (Class 100)
Staining and Color Change (after 100 h UV + 14 days immersion)	ASTM C 510	No staining/color change



Adhesion/Cohesion Under Cyclic Movement (Hockman, +100%/-50%, 10 cycles)	ASTM C 719	Pass
Peel Strength (dry/wet)	ASTM C 794	≥ 8 lbf/in (≈ 1.4 N/mm)
Continuous Water Immersion (10 weeks)	ASTM C 1247	Pass
Adhesion and Cohesion	EN 14188-2	No failure (System S, Class A, Type SL)
Hydrolysis Resistance (< 50% hardness change)	EN 14187-5	Pass
Shelf Life		12 months
Packaging		18.1 l cans, 189 l and 199.5 l drums, 600 ml tubes
Related Standards		ASTM D 5893 (Type SL), ASTM C 920 (Type S, Grade P, Movement Class 100), EN 14188-2 (System S, Class A, Type SL), FAA AC 150/5370-10 Item P-605, EN 14187-5, SS-S-200E

CE: CE marked in accordance with EN 14188-2 (DoP STN-SSSI110-0001).

